

MEGAPOXY 132 FLEXIBLE

Megapoxy 132 Flexible is a two component solventless epoxy resin. Megapoxy 132 Flexible is designed for control construction joints and high impact applications including,

Sealing Constructions Joints
Factory Floors
Parking Structures
Warehouse Floors
Ramps and Driveways
Joints in Decks etc.

Product Properties Uncured

Shelf Life	2 Years
Appearance Part A	Clear Liquid
Part B	Clear Liquid
Mix Ratio By Volume	2 Parts A 1 Part B
Pot Life (1 Litre mix)	30 Minutes at 25 C
Tack Free Time	6 Hours at 25C
Cure Time	24 hours at 25C
Specific Gravity	1.10

Properties Cured

Movement Tolerance	4 %
Hardness (Shore D)	80 - 90

Megapoxy 132 Flexible does not require priming on clean & dry, prepared surfaces. Consult our technical department for our Methods of Surface Preparation manual. As with all joints the use of backing rods and bond breaker tapes is recommended when using Megapoxy 132 Flexible.

Use this Bulletin in conjunction with Megapoxy H & 132 Technical Bulletins, which contains other important information on filler loading. However the use of rubber particles instead of silica sand is recommended for greater flexibility.

