

MEGAPOXY 34

UNDER GROUND CABLE JOINTING AND ENCAPSULATION OF ELECTRICAL COMPONENTS

DESCRIPTION

MEGAPOXY 34 is a low viscosity 100% solids epoxy resin formulation suitable for underground cable jointing and is recommended for encapsulation of instrument transformers, lighting transformers, small power transformers and coils, for electrical and electronic industries.

MEGAPOXY 34 is suitable for casting electrical switchgear components and for mechanical and chemical resistant applications. Cured MEGAPOXY 34 has excellent static and dynamic mechanical properties as well as superior electrical and dielectric properties.

Mixing Ratio	: 4 parts "A" to 3 parts "B" by volume or weight
Pot Life	: 30 Minutes at 25°C
Setting Time	: 6 Hours at 25°C
Cure Time	: 24 Hours at 25°C

PRODUCT SPECIFICATION

Megapoxy 34 conforms to AS3100-1990 including amendments 1,2 by AGL for encapsulating and potting of electrical components and cable joints.

AVAILABILITY

Megapoxy 34 is available in 2kg kits. In each 2kg kit measuring cups and stirrers are provided.

BULK SUPPLIES ARE AVAILABLE.

CURED PROPERTIES

Peak Service Temperature	: 150°C
Volume Resistivity	: 10 ¹³ ohm.cm
Dielectric Strength	: 315 kv/cm
Compressive Strength	90 MPa

