

## **GLAZECOAT**

## Single Coat Sealer For Porous Epoxy Coving

## **Technical Data Sheet**

DESCRIPTION	Megapoxy GlazeCoat is a, 100% solids, resin based, solvent-free, gel resin, that has been		
	designed as a single coat sealer for porous epoxy coving.		
	Megapoxy GlazeCoat has a suitable work-time to allow for the complete kit to be mixed and applied.		
	Megapoxy GlazeCoat is volatile organic compounds free (Nil V.O.C.)		
RECOMMENDED APPLICATIONS	<ul> <li>Sealing Sand Epoxy Grouts</li> </ul>		
	<ul> <li>Sealing Epoxy Sand Coving</li> <li>Sealing Porous Epoxy Sand Screeds</li> </ul>		
	PROPERTIES	Mixing Ratio	2.5 Parts A to 1 Part B
Working Time		30 minutes at 25°C	
Minimum Cure Time at 15°C		48 hours	
Minimum Cure Time at 25°C		24 hours	
Minimum Cure Time at 35°		12 hours	
Minimum Application Temperature		10℃	
Viscosity Part A at 25°C		138000cps	
Viscosity Part B at 25°C		130-160cps	
Viscosity Mixed at 25°C		44075cps	
Specific gravity Part A		1.00-1.05	
Specific gravity Part B		0.97-0.99	
Mixed Specific gravity		1.03	
Colour Part A		Opaque White	
Colour Part B		Clear	
Colour Mixed		Opaque White	
CURED PROPERTIES	Compressive Strength - ASTM 695	70Mpa	
	Bond Strength Concrete - ASTM 454	>3Mpa	
	Modulus of Elasticity - ASTM 695	Gpa	
	Flexural Strength - ASTM D695-96	Мра	
	Tensile Strength	Мра	
	Hardness - Barcol 935	65 Minimum	

3 Sefton Road, Thornleigh NSW 2120 Australia | P:+61 (02) 9875 3044 | E: info@megapoxy.com | megapoxy.com





## **Technical Data Sheet**

CHARATERISTICS	• VOC Free	
	Thick consistency	
	<ul> <li>Seals porous surfaces in 1 coat</li> <li>Mixes easily by hand</li> <li>Very high strength permanent bonds</li> </ul>	
	Excellent chemical resistance	
SURFACE PREPERATION	<u>Concrete</u>	
	Concrete should be free from grease and oil. If necessary, clean with industrial heavy duty	
	degreaser. When clean, remove surface laitance. This is best done by mechanical abrasion	
	such as scabbling, grit blasting or grinding. If this is not possible acid etching must be carried	
	out. Mix concentrated hydrochloric acid with equal volume of water and spread at the rate of	
	0.5 litre per square meter of concrete surface. Allow to react for about 10 minutes and wash	
	the area thoroughly and scrub with a stiff bristled broom to remove loose sand. Allow to dry	
	for 24 hours. For maximum adhesion the concrete should be surface dry.	
	Epoxy & Sand Coving and Screeds	
	Surface should be dry and damage free, all loose sand should be swept or over vacuumed from the surface.	
	Coated Surfaces	
	It is recommend to remove all coatings prior to bonding, bonding to coated surfaces will give	
	inferior bond strengths compared to bonding directly to a prepared substrate.	
	Concrete:	
	The surface may be either flame-cleaned, or mechanically treated with a scutching tool, to	
	remove all traces of paint. Complete the preparation by diamond grinding or scabbling.	
	Epoxy Coatings:	
	Steps should be taken to remove all previous epoxy sealers and coatings, surface should be	
	roughened, cleaned, making sure the surface is dust free.	
IMPORTANT INFORMATION	It is essential that the correct mixing ratio be used and that the Part A and Part B are	
	thoroughly mixed together before use. Inaccuracies and poor mixing will result in lower	
	physical properties of the cured system and, if the error is sufficiently large, the system may not	
	cure satisfactorily and discolour on ageing.	
CLEANING	To keep mixing implements and working tools clean, use Megapoxy Thinners.	
	Use disposable rubber gloves to protect hands and maintain proper industrial hygiene.	
	For further details refer to the Megapoxy GlazeCoat Safety Data Sheet.	
DACKACINIC	Maganovy ClazoCoat is available in a 14lt kits	
PACKAGING	Megapoxy GlazeCoat is available in a 14lt kits.	
	Product should be stored in cool dry store.	
TECHNICAL SERVICE	All purchasers of Megapoxy Products, are encouraged to avail themselves of our	
	Technical Service for our Megapoxy Products. The information in this Bulletin is correct at time of	
	publication, however continual research and development is being carried out and specs may change	
	without notice.	

3 Sefton Road, Thornleigh NSW 2120 Australia | P:+61 (02) 9875 3044 | E: info@megapoxy.com | megapoxy.com



